Approved For Release 1999/08/27 : CIA-RDP78-04133A000100060005-0

LABORATORY REPORT

ABBOT A. HANKS, INC.
ENGINEERS. ASSAYERS. CHEMISTS. METALLURGISTS
CONSULTING - TESTING - INSPECTING
ESTABLISHED 1868
624 SACRAMENTO STREET
SAN FRANCISCO 11, CALIFORNIA
TELEPHONE GARFIELD 1-1697

File No. 823

Lab. No. 56341 *Date* June 11, 1953

Sample Hollow Concrete Masonry Units Tests of hollow concrete masonry units sampled

Received 6-3-53 *Mark* 6-3-53

Submitted by Basalt Rock Company
8th & River Streets
Napa, California

Attention: C. W. Rollins

In accordance with your instructions and in compliance with ASTM C140-39 we have made tests of hollow concrete masonry units which our representative sampled, ~~not~~ at your Napa, California plant, on 6-3-53. Our results are as follows:

Lab. No. 56341

Material: Hollow concrete masonry Units

Source: Basalt Rock Company

Size: 7 5/8 X 15 5/8 X 7 5/8 high (1 1/4" minimum walls)

Gross Area: 119 sq. in

	Compression Strength, Psi	Absorption lbs. per Cu. ft.	Moisture content % as received
1	1341	10.0	16.2
2	1278	10.2	8.9
3	1224	10.2	8.4
4	1281	9.8	10.0
5	1340	10.1	10.4
	1293 avg.	10.1	10.8

Respectfully submitted,

ABBOT A. HANKS, INC.

By [signature]

Approved For Release 1999/08/27 : CIA-RDP78-04133A000100060005-0

FORM A-10